

Serial No. 09/961,203

LISTING OF CLAIMS:

1. (Currently amended) A ceramic carrier comprising a ~~substrate-ceramic~~ substrate and a multitude of pores or elements ~~capable of supporting that support~~ a catalyst component directly on the surface of the substrate-ceramic substrate, which wherein the catalyst component contains metal elements having NOx absorbent capacity.

2. (Original) The ceramic carrier according to claim 1, wherein the pores capable of directly supporting the catalyst component comprise at least one kind selected from among a group consisting of defects in the ceramic crystal lattice, microscopic cracks in the ceramic surface and missing defects of the elements which constitute the ceramic, and the elements capable of directly supporting the catalyst component are elements which substitute for a part of the constituent elements of the substrate ceramic.

3. (Previously presented) The ceramic carrier according to claim 1, wherein defects in the ceramic crystal lattice, which constitute the pores capable of directly supporting the catalyst component, are formed and NOx absorbent capacity is given by substituting a part of the constituent elements of the ceramic with the metal elements having NOx absorbent capacity.

4. (Original) The ceramic carrier according to claim 1, wherein NOx absorbent capacity is given by supporting the metal elements which have NOx absorbent capacity in the pores capable of directly supporting the catalyst component.

Serial No. 09/961,203

5. (Original) The ceramic carrier according to claim 1, wherein the metal element having NO_x absorbent capacity is an alkali metal element, an alkali earth metal element, a rare earth element or a transition metal element.

6. (Original) The ceramic carrier according to claim 1, wherein the substrate ceramic includes cordierite as the major component.

7. (Original) The ceramic carrier according to claim 1 wherein the carrier has a form of at least one kind selected from among a group consisting of a honeycomb, pellets, powder, a foam body, a fiber and a hollow fiber.

8. (Original) The ceramic carrier according to claim 1, wherein the pores which can directly support the catalyst component have a diameter or width 1000 times the diameter of the catalyst ion to be supported or smaller, and the density of pores is $1 \times 10^{11}/L$ or higher.

9. (Original) A ceramic catalyst body comprising the ceramic carrier of claim 1 and a catalyst component supported directly on the surface the ceramic carrier without forming a coating layer.

10. (Original) The ceramic catalyst body according to claim 9, wherein the catalyst is supported in the vicinity of the metal elements having NO_x absorbent capacity.

Serial No. 09/961,203

11. (Original) The ceramic catalyst body according to claim 9 wherein the catalyst component is a noble metal.